

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

RWAP 1359

SPECIFICATION	VALUE	TEST METHOD
Iodine Number (mg/g)	Min: 1000	ASTM
Apparent Density (g/cc)- Dry	Min: 0.50	ASTM
CTC adsorption (% by wt)	45-50	ASTM
Moisture (% by wt)	Max: 3	ASTM
Total Ash (% by wt)	Max: 1	ASTM
Hardness Number	Min: 98	ASTM
Extractable pH	6—8	ASTM
<u>Particle size 12X30 ASTM mesh</u>		
> 12mesh (1.700 mm) (% by wt)	Max: 5	ASTM
12 X 30 (1.700 mm x 0.600 mm) (% by wt)	Min: 90	ASTM
< 30 mesh (0.600 mm) (% by wt)	Max: 5	ASTM

Spec No: 8025

Date: 01.02.2019



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com